




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G03G 5/00, B44C 1/00	A1	(11) International Publication Number: WO 97/42550 (43) International Publication Date: 13 November 1997 (13.11.97)
(21) International Application Number: PCT/US97/06511 (22) International Filing Date: 16 April 1997 (16.04.97) (30) Priority Data: 08/646,913 8 May 1996 (08.05.96) US (71) Applicant: REXAM GRAPHICS INCORPORATED [US/US]; 28 Gaylord Street, South Hadley, MA 01075-2894 (US). (72) Inventors: CAHILL, Douglas, Allan; 281 Chauncey Walker Road, Lot #125, Belchertown, MA 01007 (US). BENNETT, Everett, Wyman; 210 Park Street, Easthampton, MA 01027 (US). SHI, Weitong; T5 Barrington Way, Glastonbury, CT 06033 (US). SPORBERT, Edward, William; Apartment C, 633 Pendelton Avenue, Chicopee, MA 01020 (US). TAYLOR, Alan, Richard; 2 Old Chester Road, Blandford, MA 01008 (US). TAYLOR, Dene, Harvey; 101 Old York Road, New Hope, PA 18938 (US). (74) Agent: MONROE, Bruce, M.; Ratner & Prestia, P.O. Box 7228, Wilmington, DE 19803 (US).		(81) Designated States: CA, JP, KR, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>

(54) Title: IMAGING ELEMENT HAVING A CONDUCTIVE POLYMER LAYER



(57) Abstract

An electrographic imaging element (10) useful for forming colored images is described. The element contains an imaging layer structure (12) and a support structure (14). The support structure (14) contains an electrically conductive polymeric release layer (16) formed by polymerizing a mixture containing a polymerizable, ethylenically unsaturated ammonium precursor; a polymerizable, ethylenically unsaturated, organo-silicone precursor; a polymerizable precursor containing at least two polymerizable, ethylenically unsaturated functional groups; optionally, a polymerizable, ethylenically unsaturated acidic precursor containing at least one carboxylic acid group; and, optionally, a monofunctional precursor containing one polymerizable, ethylenically unsaturated functional group. The element is particularly useful for forming large size images, such as are required for banners, billboards, and other out-of-doors advertisements.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

DESCRIPTIONIMAGING ELEMENT HAVING A CONDUCTIVE POLYMER LAYER5 FIELD OF THE INVENTION

This invention relates to elements for electrographic imaging. More particularly, this invention relates to elements for electrographic imaging comprising an electrically conductive polymeric release layer and to their
10 use in forming color images.

BACKGROUND OF THE INVENTION

In electrographic imaging a latent image of electric charge is formed on a surface of a carrier. Toner particles
15 that are attracted to the charge are applied to the surface of the carrier to render the latent image visible. The toned image is fixed, either by fusing the toner particles to the surface of the carrier, or by first transferring the toned image to a receptor and fusing, or otherwise
20 permanently affixing, the particles to the receptor.

The latent image is produced by imagewise deposition of electrical charge onto the carrier surface. Typically, charged styli, arranged in linear arrays across the width of a moving dielectric surface, are used to create the latent
25 image. Such processes are disclosed, for example, in Helmberger, U.S. Patent 4,007,489; Doggett, U.S. Patent 4,731,542; and St. John, U.S. Patent 4,569,584.

After the latent image has been created on the surface of the carrier, toner is applied to produce a toned image.
30 The toner is fixed to the surface of the carrier by heat fusing, or, if the toner is dispersed in a liquid, by drying and then, optionally, by heat fusing. When fixing is by drying only, the image is comparatively fragile and can be damaged by physical contact, abrasion, and the like.

35 Because color electrography needs only a carrier comprising a dielectric layer over a conductive support, it has, from its inception, been used for applications in which large size images are needed, such as for store graphics, posters, signs, banners, and other out-of-doors

advertisements. In these applications the need for image protection is intense. Consequently, the color electrographic art has, from the outset, endeavored to protect the image.

5 One well-known way of protecting the image is to overlaminate the image with a permanent transparent protective film to form a laminate consisting of, in order, the carrier, the image, and the transparent protective film. In this method, the image is both fixed and protected
10 between the original carrier and the transparent protective film in a single step.

In overlamination, the original carrier becomes an integral component of the final product. The carrier typically comprises a conductive base paper, which is
15 unsuited for outdoor uses, even when protected by the overlaminated transparent protective film. Thus, overlamination is generally not suitable for preparing images for outdoor applications.

Another way of using the image, which avoids having the
20 conductive base as part of the final product, is to laminate a receptor onto the toner that forms the image and then remove and discard the original carrier. In a second step, a permanent protective transparent film is laminated to the image and receptor, to form an element comprising the
25 receptor, the toner image, and the permanent protective transparent film. The toner image is fixed and protected between the receptor and the permanent protective transparent film in two steps. This process is described in Chou, U.S. Patent 5,262,259.

30 An alternative way that avoids having the conductive base as part of the final product is to laminate a receptor onto the surface of the dielectric layer which contains the toner that forms the image. Then the conductive base is removed and discarded, leaving behind the dielectric layer.
35 This forms a product, comprising the receptor, the toner image, and the dielectric layer, in which the dielectric layer now serves as a protective layer. The image is fixed and protected between the dielectric layer and the receptor in a single step. Electrographic elements useful in this

process are disclosed in Cahill, U.S. Patents 5,414,502 and 5,483,321.

If the imaged and toned dielectric layer is to be transferred to provide a protective layer for the image, the dielectric layer must be able to release from the conductive base. To enhance release, a non-conductive release layer has been provided between the dielectric layer and the conductive base, increasing the cost and manufacturing complexity for the elements and lowering the density of the image. Therefore, to reduce manufacturing cost and improve image density, a need exists for electrographic imaging elements that do not comprise a separate release layer.

SUMMARY OF THE INVENTION

The invention is an imaging element comprising a support structure and an imaging layer structure wherein the support structure is removably adhered to the imaging layer structure and wherein the support structure comprises an electrically conductive polymeric release layer having tailored optical and surface release properties. The electrically conductive release layer comprises, in polymerized form:

- (A) 1 to 80 weight parts of a polymerizable, ethylenically unsaturated ammonium precursor;
- (B) 0.1 to 10 weight parts of a polymerizable, ethylenically unsaturated, organo-silicone precursor;
- (C) 5 to 95 weight parts of a multifunctional polymerizable precursor containing at least two polymerizable, ethylenically unsaturated functional groups;
- (D) 0 to 60 weight parts of a polymerizable, ethylenically unsaturated acidic precursor containing at least one carboxylic acid group; and
- (E) 0 to 90 weight parts of a monofunctional precursor containing one polymerizable, ethylenically unsaturated functional group.

The electrically conductive polymeric release layer has a thickness of about 1 to 20 microns, an electrical

resistance between about $1 \times 10^5 \Omega/\square$ and $1 \times 10^6 \Omega/\square$, and a surface energy of between 20 and 40 dynes/cm².

In another embodiment, the invention is a method for forming an image using an imaging element of this invention.

5

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic representation of an imaging element of this invention.

FIGS. 2a and 2b are schematic representations of the support layer structure of electrographic imaging elements of this invention.

FIGS. 3a and 3b are schematic representations of the imaging layer structure of electrographic imaging elements of this invention.

FIG. 4 is a schematic representation of a preferred electrographic imaging element of this invention.

DETAILED DESCRIPTION OF THE INVENTION

IMAGING ELEMENT

The invention is an imaging element suitable for use in electrographic imaging. The element comprises an electrically conductive polymeric layer, which can be formed into high-gloss or matte coatings.

The imaging element will now be described by reference to the accompanying drawings. Throughout the specification, similar reference characters refer to similar elements in all figures of the drawings.

Referring to FIG. 1, imaging element 10 comprises imaging layer structure 12 and support structure 14. Imaging layer structure 12 has imaging surface 24 on which the image is formed. Support structure 14 comprises the electrically conductive polymeric release layer. The detailed structure of imaging layer structure 12 and of support structure 14, which is dependent on the imaging method and the intended application of the image, is described below.

ELECTROGRAPHIC IMAGING ELEMENTS

Support Structure

In one embodiment, the invention is an element suitable

for use as an electrographic imaging element. Referring to FIG. 2a, support structure 14 of electrographic imaging element 10 comprises electrically conductive polymeric release layer 16 and base 18.

5 Electrically Conductive Polymeric Release Layer

Electrically conductive polymeric release layer 16 has tailored optical, electrical, and surface release properties. The layer adheres tightly to base 18, has a high-gloss or a matte surface, has a surface resistivity of
10 typically about $1 \times 10^5 \Omega/\square$, and affords easy release. By suitable choice of concentrations of three or more polymerizable components, surface conductivity can be varied over a wide range, i.e., an electrical resistance between about $1 \times 10^5 \Omega/\square$ and $1 \times 10^{12} \Omega/\square$, without adversely affecting
15 surface release characteristics. For electrographic imaging materials an electrical resistance between about $1 \times 10^5 \Omega/\square$ and $1 \times 10^7 \Omega/\square$ is preferred. Preferably the layer has a surface energy of between 20 and 40 dynes/cm².

Electrically conductive polymeric release layer 16 is
20 prepared by radiation induced, free radical co-polymerization of three or more free-radical polymerizable materials. In this way, such polymerizable materials that would otherwise form individual polymers that are immiscible and incapable of affording defect-free coatings, can be
25 conveniently converted via copolymerization into a single phase, thus achieving "forced" compatibility and simultaneously avoiding any problems due to component migration.

Electrically conductive polymeric release layer 16 is
30 polymerized from a liquid mixture comprising three or more free-radical polymerizable materials containing one or more ethylenically unsaturated functional group(s). Based on the weight of the polymer to be formed, the liquid mixture comprises: 1 to 80 weight parts, preferably about 60 to 80
35 weight parts, of a polymerizable, ethylenically unsaturated, quaternary ammonium precursor; 0.1 to 10 weight parts, preferably about 0.2 to 2 weight parts, of a polymerizable, ethylenically unsaturated, organo-silicone precursor; and, 5 to 95 weight parts of a multifunctional polymerizable

precursor containing at least two polymerizable, ethylenically unsaturated functional groups, wherein the multifunctional polymerizable precursor is a multifunctional monomeric material, an oligomeric material or a combination thereof. [Weight parts are equivalent to weight percent.] Preferably, the polymerizable, ethylenically unsaturated, organo-silicone precursor is a polyoxyalkylene modified organo-silicone having medium to high hydrophile/lipophile balance (HLB) and dispersing ability. A medium HBL means 8-5 and a high HBL is 13-18 as defined in *Encyclopedia of Chemical Technology*, Kirk-Othmer, 3rd ed., Vol. 8, p. 911.

Optionally, the liquid mixture may also contain up to 60 weight parts of a polymerizable, ethylenically unsaturated acidic precursor containing at least one carboxylic acid group to improve conductivity of the resulting polymer; and up to 50 weight parts of an other monofunctional precursor containing one polymerizable, ethylenically unsaturated functional group to further adjust the properties of the polymer, e.g., the glass transition temperature and flexibility. Preferably, the acidic precursor has an acid number between about 100 and about 900. When the polymerizable compounds are to be polymerized using ultraviolet light, the liquid mixture typically will contain up to 10 wt.% of a photoinitiator system.




"Precursor" means a polymerizable, ethylenically unsaturated, monomeric material, oligomeric material or other like component. Thus the precursors used to form electrically conductive polymeric release layer 16 are the free radical, addition polymerizable monomeric materials, oligomeric materials or other like components, in which each precursor contains one or more ethylenically unsaturated functional group(s). Each component is further described in the following paragraphs.

A) Ethylenically unsaturated ammonium precursor:

"Ammonium precursor" means an ethylenically unsaturated, quaternary ammonium salt compound which contains an ammonium cation and an inorganic or organic salt anion. Electrical conductivity of the polymer is obtained by use of the reactive ammonium precursors such as (3-(methacryloylamino)-

propyl)trimethylammonium chloride (MAPTAC), dimethylamino-ethylmethacrylate dimethylsulfate quaternary (Ageflex® FM1Q80DMS), dimethylaminoethylacrylate methylchloride quaternary (Ageflex® FA1Q80MC), dimethylaminoethyl-
 5 methacrylate methylchloride quaternary (Ageflex® FM1Q75MC), dimethylaminoethylacrylate dimethylsulfate quaternary (Ageflex® FA1Q80DMS), diethylaminoethylacrylate dimethylsulfate quaternary (Ageflex® FA2Q80DMS), dimethyldiallyl-ammonium chloride (DMDAC), and vinylbenzyltrimethylammonium
 10 chloride, all of which are water soluble and, typically, are supplied with up to 50 wt% water. Consequently, such quaternary components are only miscible with a few very hydrophilic precursors unless a coupling solvent, such as those described below, is used.

15 "Quaternary salt precursors" typically have the following structures:



30 in which R_1 is H, methyl, or ethyl; Y is -O- or -(NR₃)-, wherein R_3 is H or a C₁-C₄ alkyl; m is an integer from 1 to 4, each R_2 individually is a C₁-C₄ alkyl group; and $[\text{X}]^-$ is an anion.

Preferably, the quaternary salt precursor contains a
 35 cation selected from the group consisting of (3-(methacryloylamino)propyl)trimethylammonium, (2-(methacryloyloxy)ethyl)trimethylammonium, (2-(acryloyloxy)ethyl)-trimethylammonium, (2-(methacryloyloxy)ethyl)methyl-diethylammonium, 4-vinylbenzyltrimethylammonium, dimethyl-
 40 diallylammonium, and mixtures thereof. The anion may be any inorganic or organic salt anion conventionally used in such quaternary salts, such as chloride, methosulfate, nitrate, and the like. It was noted that the conductivity (or

resistivity) of the coating is determined largely (but not wholly) by the molal concentration (number of moles per kilogram, all densities being close to unity) of quaternary salt present. For this reason, the most preferred
5 quaternary structure is that with the lowest molecular weight, 2-acryloyloxyethyltrimethylammonium chloride, which also is expected to polymerize more easily than a methacrylate.

B) Ethylenically unsaturated, organo-silicone
10 precursor: The ethylenically unsaturated, organo-silicone precursor provides surface release characteristics to electrically conductive polymeric release layer 16. Surprisingly, only about 0.1 to 10.0 wt. parts of this precursor is required to provide adequate surface release
15 characteristics to layer 16.

In contrast to the ethylenically unsaturated ammonium precursors described above, ethylenically unsaturated, organo-silicone compounds typically are immiscible with water. The term "immiscible" has its conventional meaning,
20 i.e., a two-phase liquid mixture in which each liquid is insoluble or partially soluble in the other liquid and wherein each separate liquid phase is separated from the other by a common liquid-liquid interface, such as a suspension, dispersion, colloid, and the like.

25 Typically, the polymerizable, ethylenically unsaturated, organo-silicone is an acrylated silicone such as an acrylated-oxyalkylene-silicone wherein the alkylene is ethylene, propylene or a combination thereof, e.g., Ebecryl® 350 and Ebecryl® 1360 which have been discovered to have
30 surfactant properties. From their cloud point behavior, water solubility, and infrared spectra, Ebecryl® 350 and Ebecryl® 1360 are believed to be acrylated polyoxyalkylene silicon copolymers wherein the solubilizing polyether units are derived from polyethylene glycol, polypropylene glycol,
35 or a mixture of the two polyethers. The simpler acrylated polydimethylsiloxanes such as Goldschmidt RC-726, are commonly employed in the release coating industry but are not water soluble. However, such acrylated polydimethylsiloxanes can be employed, particularly, if used in

conjunction with an acrylated surfactant type silicone polymer such as Ebecryl® 350 or Ebecryl® 1360.

"Acrylated-oxyalkylene-silicone" means an organo-silicone precursor having one or more acrylate or methacrylate groups bonded thereto, and one or more oxyalkylene groups incorporated therein or pendant thereto. The oxyalkylene group has the structure:



in which R is hydrogen or methyl.

Such acrylated-oxyalkylene-silicones may be used alone or in combination with an acrylated silicone. Acrylated-oxyalkylene-silicones of this type include a polyacrylated polydimethylsiloxanepolyether copolymer having a viscosity of 200-300 centipoise at 25°C (Ebecryl® 350); a hexaacrylate of a polydimethylsiloxanepolyether copolymer having a viscosity of 1000-3000 centipoise at 25°C (Ebecryl® 1360); and acrylate derivatives of hydroxy endcapped polydimethylsiloxanepolyether copolymers such as Silwet® L 7604, Coat-o-Sil® 3500 and Coat-o-Sil® 3501. Although the acrylated-silicone class of compounds (e.g., acrylated polydimethylsiloxane) are not water miscible nor compatible with quaternary salts, it was discovered that acrylated-oxyalkylene-silicones were acrylated surfactants of the siloxane-g-polyether type and, furthermore, were of high enough hydrophile/lipophile balance to have significant water solubility. Accordingly, when such acrylated silicone surfactants are incorporated into the quaternary containing coating mixtures, a solution can be obtained in some formulations (precursor rich formulations, especially those with a coupling solvent - see Example 7) and in others a usefully stable dispersion (formulations containing oligomeric acrylates to improve cure rate and physical properties - see Example 8), each of which can be readily cured to a dry film.

The efficacy of quite small amounts of such an acrylated silicone surfactant, 1-4 wt.%, in providing release properties toward aggressive pressure-sensitive adhesives is outstanding. It has been noted that the efficacy of the acrylated silicone release properties seems

to be affected by the quaternary salt concentration being better with 28-30 wt.% quaternary than with 20-25 wt.% present; and that the acrylated silicone, Ebecryl® 350, provides good release at 1-4 wt.% all by itself and use of Ebecryl® 1360 provides no significant advantage aside from increasing the stability of dispersion type mixes. It was also noted that Ebecryl® 1360 acrylated siloxane (found to be a high HLB siloxane-g-polyether surfactant) caused significant and undesirable viscosity exaltation in some mixes compared to analogous formulations using Ebecryl® 350 (2400 cps. vs. 1400 cps.).

C) Multifunctional polymerizable precursor: The multifunctional polymerizable precursor functions as a free radical crosslinking agent to accelerate growth of the polymer during polymerization. The multifunctional polymerizable precursor may be a multifunctional monomeric material, an oligomeric material, or a combination thereof. The term "multifunctional" means two or more ethylenically unsaturated functional groups capable of free radical addition polymerization. "Monomeric materials" hereinafter are identified as "monomers". The term "oligomer" or "oligomeric", has its conventional meaning, a polymer whose properties change with the addition of one or a few repeating units. As such an oligomer functions as a pre-polymer having ethylenic groups capable of further polymerization. "Oligomeric materials" are identified as "oligomers".

Typical multifunctional monomers useful in forming electrically conductive polymeric release layer 16 include, for example, trimethylolpropane triacrylate, pentaerythritol triacrylate, pentaerythritol tetraacrylate, pentaerythritol tetramethacrylate, ethoxylatedtrimethylolpropane triacrylate, glycerolpropoxy triacrylate, ethyleneglycol diacrylate, tripropyleneglycol diacrylate, and tetraethyleneglycol diacrylate. Particularly useful monomers are the ethoxylated precursors, such as ethoxylatedtrimethylolpropane triacrylate (TMPEOTA).

Oligomers typically are used in the coating dispersions to achieve a cure rate rapid enough to meet polymer

productivity goals. The criteria used to select useful oligomers are: viscosity, compatibility, glass transition temperature (T_g), degree of functionality, and coating glossiness. Illustrative of such oligomers are the

5 commercial products tabulated along with their properties in the following tables. Typical oligomers useful in forming electrically conductive polymeric release layer 16 include, but are not intended to be limited thereby, acrylated urethanes, polyesters, and polyepoxides; and acrylics.

10 Useful acrylated urethanes include: Ebecryl® 230, an aliphatic urethane; Ebecryl® 244, an aliphatic urethane & 10% 1,6-hexanediol diacrylate; Ebecryl® 265, an aliphatic urethane & 25% tripropyleneglycol diacrylate; Ebecryl® 270, an aliphatic urethane; Ebecryl® 285, an aliphatic urethane &
 15 25% tripropyleneglycol diacrylate; Ebecryl® 4830, an aliphatic urethane & 10% tetraethyleneglycol diacrylate; Ebecryl® 4833, an aliphatic urethane & 10% N-vinyl-2-pyrrolidone; Ebecryl® 4834, an aliphatic urethane & 10% N-vinyl-2-pyrrolidone; Ebecryl® 4881, an aliphatic urethane &
 20 10% tetraethyleneglycol diacrylate; Ebecryl® 4883, an aliphatic urethane & 15% tripropyleneglycol diacrylate; Ebecryl® 8803-20R, an aliphatic urethane & 20% tripropyleneglycol diacrylate & 8% ethoxyethoxyethyl acrylate; and Ebecryl® 8803, an aliphatic urethane.
 25 Properties of these products are given in Table 1.

Table 1

	<u>Product</u>	<u>Viscosity¹</u>	<u>Mol.Wt.²</u>	<u>Groups³</u>	<u>Tg⁴</u>
30	Ebecryl® 230	30-50 @ 25°	-	2	39
	Ebecryl® 244	7.0-9.0 @ 60°	2000	2	-
	Ebecryl® 265	25-45 @ 25°	2000	3	38
	Ebecryl® 270	2.5-3.5 @ 60°	1500	2	-
35	Ebecryl® 285	20-30 @ 25°	1200	2	42
	Ebecryl® 4830	2.5-4.5 @ 60°	1200	2	42
	Ebecryl® 4833	2.0-3.0 @ 60°	1200	2	47
	Ebecryl® 4834	3.0-4.0 @ 60°	1600	2	32
	Ebecryl® 4881	5.3-8.1 @ 60°	2000	2	44
40	Ebecryl® 4883	2.8-4.2 @ 60°	1600	2	47
	Ebecryl® 8800-20R	1.8-3.0 @ 65°	1600	2.5	59
	Ebecryl® 8803	25-35 @ 65°	2300	2.4	52

45 1. Viscosity is given in "10 poise" units & temperature is in "°C".

2. Molecular weight is based on neat undiluted oligomer.

3. "Groups" is the number of ethylenic functional groups.
 4. "Tg" is glass transition temperature given in °C.

Useful polyester oligomers include: Ebecryl® 450, a fatty acid modified polyester; Ebecryl® 505, an unsaturated polyester & 40% tripropyleneglycol diacrylate; Ebecryl® 509, an acid modified unsaturated polyester & 30% 2-hydroxyethyl-methacrylate; Ebecryl® 524, an acid modified polyester & 30% 1,6-hexanediol diacrylate; Ebecryl® 525, an acid modified polyester & 40% tripropyleneglycol diacrylate; Ebecryl® 584, a chlorinated polyester & 40% 1,6-hexanediol diacrylate; Ebecryl® 585, a chlorinated polyester & 40% tripropylene-glycol diacrylate; Ebecryl® 810, a tetrafunctional polyester acrylate; Ebecryl® 1810, a tetrafunctional polyester acrylate; and Photomer® 5018, an aliphatic tetrafunctional polyesteracrylate. Properties of these products are given in Table 2.

Table 2

Product	Viscosity ¹	Mol.Wt. ²	Groups ³	Tg ⁴
Ebecryl® 450	6-8 @ 25°	-	6	
Ebecryl® 505	1.75-2.25 @ 60°	-		45
Ebecryl® 509	6-8 @ 25°	-		
Ebecryl® 524	55-65 @ 25°	1000		
Ebecryl® 525	35-45 @ 25°	1000		
Ebecryl® 584	1.5-2.5 @ 25°	-		44
Ebecryl® 585	4.2-5.2 @ 25°	-		29
Ebecryl® 810	0.45-0.65 @ 25°	900	4	31
Ebecryl® 1810	0.45-0.65 @ 25°	900	4	32
Photomer® 5018	0.7-1.4 @ 25°	1000	4	0

1. Viscosity is given in "10 poise" units & temperature is in "°C".
 2. Molecular weight is based on neat undiluted oligomer.
 3. "Groups" is the number of ethylenic functional groups.
 4. "Tg" is glass transition temperature given in °C.

Useful polyepoxy oligomers include: Ebecryl® 605, a bisphenol A epoxy diacrylate & 25% tripropyleneglycol diacrylate; Ebecryl® 616, an epoxy dimethacrylate oligomer & 25% trimethylolpropane triacrylate; Ebecryl® 860, an epoxidized oil acrylate; Ebecryl® 1608, a bisphenol A epoxy acrylate & 20% propoxylated glycerol triacrylate; Ebecryl® 3200, a blend of aliphatic and aromatic acrylated epoxy resins; Ebecryl® 3201, an acrylated epoxy resin; Ebecryl®

3605, a partially acrylated bisphenol A epoxy resin; Ebecryl® 3700-20T, a bisphenol A epoxy acrylate & 20% trimethylol-propane triacrylate; Ebecryl® 3701-20T, a modified bisphenol A epoxy acrylate oligomer & 20% trimethylolpropane triacrylate; and Ebecryl® 3700, a bisphenol A epoxy diacrylate. Properties of these products are given in Table 3.

Table 3

Product	Viscosity ¹	Mol.Wt. ²	Groups ³	Tg ⁴
Ebecryl® 605	6.5-8.5x10 ³ @ 25°	525	2	65
Ebecryl® 616	20-30 @ 25°	555	2	82
Ebecryl® 860	19-31 @ 25°	1200	3	13
Ebecryl® 1608	0.9-1.1 @ 60°	525	2	67
Ebecryl® 3200	1.5-3.0 @ 25°	435	1.6	48
Ebecryl® 3201	2.5-5.0 @ 25°	426	1.9	8
Ebecryl® 3605	0.5-0.8 @ 65°	450	1	43
Ebecryl® 3700-20T	.43-.63 @ 65°	524	2	75
Ebecryl® 3701-20T	.85-1.25 @ 65°	840	2	62
Ebecryl® 3700	1.8-2.8 @ 65°	524	2	65

1. Viscosity is given in "10 poise" units & temperature is in "°C".

2. Molecular weight is based on neat undiluted oligomer.

3. "Groups" is the number of ethylenic functional groups.

4. "Tg" is glass transition temperature given in °C.

Useful acrylic oligomers include: Ebecryl® 745, an acrylic oligomer & 23% 1,6-hexanediol diacrylate & 23% tripropylene-glycol diacrylate; Ebecryl® 754, an acrylic oligomer & 30% 1,6-hexanediol diacrylate; and Ebecryl® 1755, an acrylic oligomer & 35% tripropyleneglycol diacrylate. Properties of these materials are given in Table 4.

Table 4

Product	Viscosity ¹	Mol.Wt. ²	Groups ³	Tg ⁴
Ebecryl® 745	25-35 @ 25°			30
Ebecryl® 754	70-80 @ 25°			22
Ebecryl® 1755	70-80 @ 25°			15
Ebecryl® 860	19-31 @ 25°	1200	3	13

1. Viscosity is given in "10 poise" units & temperature is in "°C".

2. Molecular weight is based on neat undiluted oligomer.

3. "Groups" is the number of ethylenic functional groups.

4. "Tg" is glass transition temperature given in °C.


Review of general properties and characteristics of a

wide range of oligomeric materials above, suggests that epoxy oligomers would be useful because of their rapid cure rates and ability to provide high gloss. However, since the majority of epoxy oligomers have rather high viscosity at room temperature (e.g., 10,000-150,000 cps.) and T_g about 55-67°C, for purposes of coatability it is considered necessary to include a low viscosity diluent with a low T_g to insure adequate flexibility. Thus solutions of oligomer in 20 to 40 wt.% di- or trifunctional diluent are useful.

In a less complicated formulation, a single oligomer may be chosen such as a tetrafunctional aliphatic polyester with T_g of 0°C and viscosity at 25°C of 400-700 cps (Photomer® 5018).

D) Ethylenically unsaturated acidic precursor: The acidic precursor functions to further enhance the electrical conductivity of the polymeric material. Typical acid precursors that are useful in forming electrically conductive polymeric release layer 16, but are not intended to be limited thereby, acrylic acid, itaconic acid, β-carboxyethylacrylate, 2-(acryloyloxy)ethyl-o-phthalate, 2-(acryloyloxy)ethylmaleate, 2-(acryloyloxy)ethyl-succinate, 2-(methacryloyloxy)ethyl-succinate, 2-(methacryloyloxy)-ethyl-maleate, and 2-(acryloyloxy)propylmaleate; and carboxylated additives having acid nos. of 100 to 900, such as Ebecryl® 169 and Ebecryl® 170.

The acidic maleate and succinate acrylic precursors have the structure:



wherein R₁ is H, methyl, or ethyl; n is an integer from 1 to 4; ..A.. is a carbon-carbon double bond or single bond, wherein when ..A.. is a double bond n is 1 and when ..A.. is a single bond n is 2.

These materials are particularly useful precursors in the preparation of the polymeric materials. Preferred acidic precursors are the low molecular weight acidic acrylic precursors, β-carboxyethylacrylate and 2-(acryloyl-

oxy)ethylmaleate. When an acidic precursor is used in the preparation of the polymeric material, about 6 to 60 wt. parts of the acidic precursor is typically present in the polymer.

- 5 E) Other monofunctional precursor: The other monofunctional precursor contains one polymerizable, ethylenically unsaturated functional group. It functions to further adjust the properties of layer 16, e.g., flexibility and glass transition temperature, and as a polymerizable co-
10 solvent for the components of the liquid polymerizable mixture used to form the layer. The term "other monofunctional precursor" excludes the ammonium precursors, organo-silicone precursors and acidic precursors, each of which may also contain only one polymerizable, ethylenically
15 unsaturated functional group.

The other monofunctional precursor typically is a low viscosity liquid. When the polymerizable mixture is to be coated as a solution, the other monofunctional precursor typically contains a hydrophilic group. Typical useful
20 other monofunctional precursors include, for example, N-vinylpyrrolidone, 2-hydroxyethylacrylate, tetrahydrofurfurylacrylate, 2-hydroxyethylmethacrylate, tetrahydrofurfurylmethacrylate, 2-hydroxypropylacrylate, 2-(2-ethoxyethoxy)ethylacrylate, 2-cyanoethylacrylate, and
25 2-hydroxypropylmethacrylate. When an other monofunctional precursor is used in the preparation of the polymeric material, about 10 to 50 wt. parts of the material typically are present in the polymer.

- F) Other components: The composition may comprise a
30 photoinitiator to facilitate copolymerization of the mixture. When the polymerizable mixture is to be cured by irradiation with ultraviolet radiation, it may comprise a free radical generating initiating system activatable by ultraviolet radiation. When the mixture is to be cured by
35 electron beam irradiation, a photoinitiating system is not required.

Suitable photoinitiating systems have been described in "Photoinitiators for Free-Radical-Initiated Photoimaging Systems," by B. M. Monroe and G. C. Weed, Chem. Rev., 93,

435-448 (1993) and in "Free Radical Polymerization" by K. K. Dietliker, in **Chemistry and Technology of UV and EB Formulation for Coatings, Inks, and Paints**, P. K. T. Oldring, ed, SITA Technology Ltd., London, 1991, Vol. 3, pp. 59-525. Preferred free radical photoinitiating compounds include benzophenone; 2-hydroxy-2-methyl-1-phenylpropan-1-one (Darocur® 1173); 2,4,6-trimethylbenzoyldiphenylphosphine oxide (Lucerin® TPO); 2,2-dimethoxy-2-phenylacetophenone (benzildimethyl ketal, BDK, Irgacure® 651, Lucirin® BDK); 2-methyl-1-[4-(methylthio)phenyl]-2-morpholinopropanone-1 (Irgacure® 907); 1-hydroxycyclohexylphenyl ketone (HCPK, Irgacure® 184); bis(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentylphosphine oxide; and combinations thereof. Preferred mixed photoinitiators include a 50:50 blend of 2-hydroxy-2-methyl-1-phenylpropan-1-one and 2,4,6-trimethylbenzoyldiphenylphosphine oxide (Darocur® 4265); and a 25:75 blend of bis(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentylphosphine oxide and 2-hydroxy-2-methyl-1-phenylpropan-1-one (CGI 1700).

Before irradiation, the unpolymerized material typically contains about 1 to 10 parts by weight, more typically about 3 to 8 parts by weight, of the photoinitiator, based on the total weight of the polymerizable materials.

The composition may also comprise particles of a matting agent to provide a matte finish to the conductive layer. Particles of average diameter in the range of about 1 μm to about 15 μm are suitable. Typically 1 to 20 wt.%, preferably 5 to 15 wt.%, of matting agent is present in the composition. A preferred matting agent is amorphous silica.

Base

Base 18 functions as a support to the superposed layers. It may be any web or sheet material possessing suitable flexibility, dimensional stability, and adherence to electrically conductive polymeric release layer 16. The base typically has a resistivity of about 1 to 30 meg-ohm/sq.

Suitable web or sheet materials for the base are flexible polymeric films, such as polyethylene terephthalate film, or a foraminous material, such as a paper sheet,

treated to be electrically conductive or semi-conductive. Other suitable materials are metal foils, metalized polymeric films, such as polyethylene terephthalate films having a metallic coating thereon, conductive paper
5 sheeting, and the like. The web or sheet may also be surface treated or coated with a material to enhance desired surface characteristics.

Back Side Conductive Layer

The support structure may also comprise a back side
10 conductive layer. Referring to FIG. 2b, support structure 14 comprises electrically conductive polymeric release layer 16, base 18, and optional back side conductive layer 20. Back side conductive layer 20 preferably comprises a film-forming material which may be an organic material, e.g.,
15 such as a cation type styrene-methacrylate copolymer having an electrical resistivity of about 1 to 30 meg-ohm/□. Other suitable film-forming, organic materials include polymeric quaternary ammonium compounds, polystyrene sulfonic acid, polymeric matrices capable of ionizing inorganic
20 electrolytes contained therein, and the like. The film-forming, organic material may be used alone or with conductive, inorganic materials and/or metals dispersed therein, e.g., such as tin oxide, aluminum and the like.

Imaging Layer Structure

25 Referring to FIG. 3a, imaging layer structure 12 of the electrographic imaging element comprises adhesive layer 13 with imaging surface 24, dielectric layer 15, and protective layer 17.

Adhesive Layer

30 Adhesive layer 13 functions to permanently adhere the image to a receptor following formation of the latent electrostatic image and toning to produce the image. Adhesive layer 13 comprises a substantially tack-free, thermal adhesive that is activated at a pressure and a
35 temperature above the normal ambient pressure and temperature of the imaging element prior to use. The adhesive may be chosen from a variety of conventional thermal adhesive materials. Typically, the thermally activated adhesive material is comprised of thermoplastic

polyurethanes; polycaprolactone; acrylic copolymers; and combinations thereof. Representative thermally activated adhesive materials include Morthane® CA-116 urethane resin (Morton International); Tone® Polymer P767E biodegradable plastic resin (Union Carbide); and Elvax® 240 vinyl resin (Du Pont Chemicals). Adhesive layer 13 is transparent in at least one region of the visible spectral region and typically is transparent throughout the visible spectral region. Adhesive layer 13 typically has a thickness of about 2-6 μm , preferably about 3-4 μm .

Adhesive layer 13 may comprise photostabilizers that protect both the layer and the underlying image from damage by ultraviolet light. Typically photostabilizers include materials that strongly absorb ultraviolet radiation, such as 2-hydroxybenzophenones, oxalanilides, aryl esters and the like, as well as hindered amine light stabilizers, such as bis(2,2,6,6-tetramethyl-4-piperidinyl) sebacate (Tinuvin® 770) and the like; and combinations thereof. Materials that do not absorb strongly in the visible region of the spectrum are preferred.

Imaging surface 14 of adhesive layer 13 may be rough to ensure good transfer of charge during passage of the element under the stylus bar during imaging. This roughness can be obtained by including in the layer particles sufficiently large to give surface irregularities to the layer. Particles of diameter in the range of about 1 μm to about 15 μm are suitable. Particle composition and size are chosen to give the required dielectric constant to the layer as well as the appropriate surface topography and abrasive properties to the layer.

Dielectric Layer

Dielectric layer 15 may be any conventional film-forming material with a dielectric constant of about 2 to about 5. The dielectric layer typically comprises one or more polymers selected from polyvinylacetate, polyvinylchloride, polyvinylbutyral, polymethylmethacrylate, styrenated acrylics, styrene acrylonitrile, and similar

materials. Other ingredients may be chosen from waxes, polyethylene, alkyd resins, nitrocellulose, ethyl cellulose, cellulose acetate, shellac, epoxy resins, styrene-butadiene copolymers, chlorinated rubbers, polyacrylates, and the like. Dielectric layer 15 typically has a thickness of about 1 μm to about 20 μm , preferably about 3 μm to about 10 μm .

Combined Dielectric/Adhesive Layer

In a preferred embodiment, the electrographic imaging element comprises a combined dielectric/adhesive layer that is substantially tack-free at ambient temperature and whose adhesive properties are activated at a temperature above ambient. Referring to FIG. 3b, imaging layer structure 12 of the electrographic imaging element comprises combined dielectric/adhesive layer 11 and protective layer 17. Combined layer 11 typically comprises one or more polyesters; polyurethanes; polyamides; polyolefins; polycarbonates; polystyrenes; and/or polymers or copolymers of acrylic or methacrylic acids, esters, amides, or the like (such as polymethylmethacrylate), styrenes, acrylonitriles, vinyl esters, alkyd substituted vinyl esters, vinyl alcohol, vinyl acetals (e.g., polyvinyl butyral), vinyl chloride, vinyl fluoride, vinylidene chloride, 1,4-dienes (e.g., butadiene, isoprene and the like); ethylene/vinyl alcohol copolymers; copolymers of styrene with acrylic and methacrylic monomers; modified cellulosic resins such as cellulose acetate and cellulose acetate butyrate; block copolymer thermoplastic rubbers (e.g., styrene/ethylene/butylene/styrene block copolymer); and blends of the above. Elements comprising a combined dielectric/adhesive layer are disclosed in Cahill, U.S. Patent 5,483,321. As described above, the combined dielectric/adhesive layer is transparent in at least one region of the visible spectrum, and may comprise photostabilizers and/or particles in the range of about 1 μm to about 15 μm . Layer 11 typically has a thickness of about 1 μm to about 20 μm , preferably about 3 μm to about 10 μm .

Protective Layer

Protective layer 17 is a polymeric film material which is resistant to scratching and abrasion as well as to environmental components and contaminants. It is permanently adhered to dielectric layer 15 or to combined dielectric/adhesive layer 11, but is removably adhered to electrically conductive release layer 16.

Protective layer 17 is transparent in at least one region of the visible spectral region and typically is transparent throughout the visible spectral region. Polymeric materials useful in making this layer include polyvinyl chloride; polyvinyl butyral; cellulose acetate propionate; cellulose acetate butyrate; polyesters; acrylics; polyurethanes; styrene copolymers, such as styrene/acrylonitrile; fluoropolymers; and combinations thereof. Protective layer 17 may also contain photostabilizers, such as those described above. To prevent distortion of the underlying image when it is viewed through the protective layer, materials that do not absorb strongly in the visible region of the spectrum are preferred.

At times it is desired to provide a range of surface finishes from highly glossy to matte. This may be done by controlling the outermost surface of protective layer 17. This surface replicates the surface of the release layer with which it is in contact prior to lamination and separation, as discussed later on in this description. Thus if the release layer has a rough texture, or contains any other relief pattern, the final image will appear matte, and if the release layer surface texture is smooth, the final image will be glossy.

Alternatively, protective layer 17 may be provided with a matte surface. This matte surface can be obtained by including in the layer particles sufficiently large to give surface irregularities to the layer. Particles of average diameter in the range of about 1 μm to about 15 μm are suitable. This layer typically has a thickness in the range of about 0.5 μm to about 10 μm and preferably in the range

of about 1 μm to about 4 μm . A preferred matting agent is amorphous silica.

A preferred protective layer consists essentially of a fluoropolymer and an acrylic polymer. Fluoropolymer refers to polymers whose structure comprises fluorine atoms covalently bonded to carbon atoms. As is well known to those skilled in the art, such polymers can be prepared by polymerization of fluorinated monomers, such as tetrafluoroethylene, hexafluoropropylene, vinylidene fluoride, perfluorovinyl ethers, and vinyl fluoride, with each other and/or with non-fluorinated monomers, such as ethylene.

Fluoropolymers that may be used in the protective layer are those that can be coated from a homogenous solution and yet have a relatively low surface energy. The fluoropolymer must be sufficiently soluble in a coating solvent that a homogeneous coating solution comprising the fluoropolymer and the acrylic polymer can be formed. The coating solvent must be fugitive, that is, it must have a sufficiently high vapor pressure that it can be removed following coating of the protective layer. Preferred coating solvents are fugitive ketones, such as acetone, methyl ethyl ketone, methyl propyl ketone, methyl butyl ketone, methyl *i*-butyl ketone, and cyclohexanone. Small amounts of fugitive co-solvents may be used, provided that the ability of the solvent to form a homogeneous coating solution comprising the fluoropolymer and the acrylic polymer is not adversely affected.

The fluoropolymer should have a surface energy of 16 to 30 dynes/cm. This surface energy is sufficiently low to provide the layer with the desired protective properties. Copolymers of vinylidene fluoride and tetrafluoroethylene may be used. Fluoropolymers having a high content of vinylidene fluoride (i.e., greater than 30% by weight) have good stability in organic solvents. As a result, the application and formation of a coherent sealing film is facilitated without causing damage to the underlying layers

of the element. A preferred fluoropolymer is Kynar® SL, a copolymer of vinylidene fluoride and tetrafluoroethylene. Polymers of perfluorovinyl ethers, sold under the tradename of Lumiflon® (ICI Americas, Wilmington, DE), may also be
5 useful.

In combination with certain concentrations of acrylic polymers, fluoropolymers attain good adhesive quality to the combined adhesive and dielectric layers of the electrographic element without apparent loss of their
10 advantageous protective qualities. The acrylic polymer should be compatible with the fluoropolymer. Useful acrylic polymers include polymers and copolymers of esters of acrylic acid and methacrylic acid, such as methyl acrylate, methyl methacrylate, ethyl acrylate, ethyl methacrylate,
15 propyl acrylate, propyl methacrylate, butyl acrylate, butyl methacrylate, and similar monomers. These materials can be prepared by polymerization techniques well known to those skilled in the art and are sold under of a variety of tradenames, including Acryloid® (Rohm and Haas) and
20 Elvacite® (Du Pont). A preferred acrylic polymer is Acryloid® A-101, methyl methacrylate acrylic polymer.

A protective layer comprising a mixture of a fluoropolymer and acrylic polymer at weight ratios ranging from about 65:35 to about 85:15, fluoropolymer to acrylic
25 polymer, provides adequate protection from hazards as well as good adhesion. A ratio of about 75:25, fluoropolymer to acrylic polymer, is preferred. The protective layer typically has a dry thickness of about 0.5 to 5 micrometers, preferably about 1.0 to 2.0 micrometers. The protective
30 layer should have a surface energy less than 50 dynes/cm, preferably less than 45 dynes/cm, more preferably less than 40 dynes/cm.

Referring to FIG. 4, a preferred embodiment of imaging element 10, suitable for use in electrographic imaging
35 processes, comprises imaging layer structure 12, made up of combined dielectric/adhesive layer 11, and fluoropolymer/-acrylic protective layer 17, and support structure 14, made

up of electrically conductive release layer 16, and base 18.

ELEMENT PREPARATION

Electrographic element preparation will be described
5 with reference to the preferred embodiment depicted in FIG.
4. Those skilled in the art will readily appreciate that
elements comprising additional or different layers can be
prepared by appropriate modifications of this procedure.

Electrically conductive release layer 16 is prepared by
10 coating a liquid mixture comprising the precursors onto base
18 and, following coating, curing the layer either with
ultraviolet or with electron beam radiation.

The liquid precursor mixture typically is coated as a
solution or a dispersion of the components in the coating
15 solvent. When the liquid mixture is coated as a dispersion
the coated dispersion typically is hazy. The coated
dispersion, upon curing, typically forms a transparent,
continuous, defect-free, polymeric film. In addition,
metastable dispersions may be used when separation time of
20 the components is in hours and the dispersion is stirred
before and during coating.

In some instances, if necessary, a coupling solvent can
be added to form a solution, so that the liquid mixture may
be coated as a solution. Typically about up to about 40
25 weight parts of the fugitive coupling solvent may be added
to the liquid mixture. "Fugitive coupling solvent" refers
to water, a water miscible organic solvent, or a mixture
thereof, which is lost after the cure. Unlike solvent based
coating solutions where the solvent forms a major component
30 of the solution, the coating solutions require only a
limited amount of coupling solvent to form a single phase
solution. Typically, the coupling solvent is removed from
the coating during or after curing. Useful coupling
solvents include diethylene glycol monoethyl ether,
35 diethylene glycol monobutyl ether, tetrahydrofurfuryl
alcohol, γ -butyrolactone, 1-methoxy-2-propanol, and
combinations thereof.

The liquid mixtures are coatable by a variety of well known techniques, such as: laboratory manual coating and full scale production machine coating including coating with wire wound or smooth (#0) Mayer rods; direct gravure or offset gravure, which are especially useful for depositing very low coating weight in the order of 0.2 to 5 g/m²; and roll, slot, spray, dip and curtain coating and the like. Although the viscosity of the liquid mixture may vary widely depending on the coating method, typically coating viscosity is from about 300 to about 2000 cps. at 25°C.

"Cure" refers to polymerization and/or crosslinking of the ethylenically unsaturated precursors by the free-radical addition process. Cure is accomplished by exposing a photoinitiator containing coating to intense ultraviolet light sources such as those available from AETEK International (Plainfield, IL) or Fusion U.V. Curing Systems, Inc. (Rockville, MD). Exposure may be carried out either in sheet form, as in the AETEK laboratory units, or in continuous web form, as on production scale coating machines having an ultraviolet curing station following the coating head. The conditions to obtain complete dry-to-touch through cure will depend upon a number of factors such as the nature and amount of ammonium precursor present, oligomer content, crosslinking precursor concentration, nature and amount of other polymerizable components present, nature and amount of photoinitiator present, coating thickness, line speed and lamp intensity, and the presence or absence of an inert atmosphere.

Protective layer 17 is coated over cured dielectric/release layer 16. The fluoropolymer/acrylic resin layer protective coating is applied using a fugitive solvent. A suitable fugitive solvent is methyl ethyl ketone, although other solvents, such as ethyl acetate as well as acetone and other fugitive ketone can be used.

Combined dielectric/adhesive layer 11 is coated over protective layer 17. Alternatively, if an element that does not comprise a protective layer is desired, combined

dielectric/adhesive layer 11 may be coated directly over cured electrically conductive release layer 16. Preparation of elements comprising a combined dielectric/adhesive layer is described in Cahill, U.S. Patent 5,483,321.

5

IMAGE FORMATION

Referring to FIG. 1, the image is produced by forming a latent image of charge on imaging surface 24 of imaging element 10, toning the latent image, laminating a receptor to imaging surface 24, and removing support structure 14 to from image comprising, in order, imaging layer structure 12, the toned image, and the receptor. Image formation will be described with respect to the preferred electrographic element depicted in FIG. 4.

A latent image is first formed by charge deposition on the surface of combined dielectric/adhesive layer 11. The latent image is then toned with an appropriate toner. Any conventional electrographic process may be used to form such image and to apply toner particles. Electrographic processes, and the associated apparatus, are disclosed in Helmberger, U.S. Patent 4,007,489; Doggett, U.S. Patent 4,731,542; and St. John, U.S. Patent 4,569,584.

When a multi-colored image is desired, the imaging and toning steps are repeated with additional toners of different colors, in either sequentially arranged imaging and toning stations or by passing the element under the same imaging station and replacing the toner in the toning station. Color reproduction usually requires three and preferably four different color toners to render a pleasing and accurate facsimile of an original color image. The selection of toner colors and the creation of the different images whose combination will provide such accurate rendition of an original image is well known in the art.

After the image has been produced, a receptor is laminated to the surface of the imaged electrographic element under an applied pressure of about 0.5 kg/cm² (7 p.s.i.) to about 100 kg/cm² (1422 p.s.i.) or more to form an element consisting of, in order, base 18, polymeric release

layer 16, protective layer 17, combined dielectric/adhesive layer 11, the toned image, and the receptor. Suitable means that may be used to apply pressure include platen presses; counterpoised, double roll, laminating devices; scanning, 5 single roll, laminating devices; vacuum laminating devices; and the like. When the receptor has an air impervious surface, roll laminating devices are preferred because they readily minimize air entrapment between the image and the receptor. Vacuum may be used to eliminate air entrapment. 10 When the receptor is rigid and roll laminating devices are used, the imaged electrographic element typically is pressure laminated to the receptor.

The receptor typically functions as the final support for the imaged electrographic element. The receptor may be 15 any surface upon which an electrographic image is desired. Typically, it is a web or sheet material possessing dimensional stability and adherence properties to the activated adhesive properties of combined dielectric/adhesive layer 11. It may be a flexible polymeric film, 20 such as polyethylene terephthalate film; a foraminous material, such as a paper or textile fabrics; metal films or webs, such as aluminum, steel, tin-plate; or any composites or laminates thereof. The receptor may also be a rigid or semi-rigid sheeting or plate, such as sheeting or plates of 25 metal, glass, ceramic, plastic, cardboard, or any composites or laminates thereof. It may vary in size from that of a photographic print, e.g., having an area of about 30 cm² or less, to that of banners and billboards, e.g., having an area of about 70 m² or greater. The receptor may be surface 30 treated or coated with a material to enhance desired surface characteristics.

Lamination produces strong adhesion between the toned electrographic element and the receptor. Heat is used during lamination to raise the temperature of combined 35 dielectric/adhesive layer 11 from ambient temperature (e.g., room temperature), where it is substantially tack-free, to a temperature at which the adhesive properties are activated.

Heat may be applied prior to and/or concurrently with the application of pressure. For example, combined dielectric/-adhesive layer 11 and the receptor may be heated by radiant or contact heaters and then laminated while hot.

5 Alternatively the pressure means itself may also function as a heater, such as a hot roll laminator, or both prior and concurrent heating may be used in combination. Preferably, a laminating temperature of about 100°C or greater is employed.

10 Next the support structure, comprising base 18 and electrically conductive release layer 16, is removed from the element formed by lamination, exposing protective layer 17. Typically, base 18 is peeled with a peel force directed at an angle of 90° or more from the surface of protective
15 layer 17. The peel rate and the peel force are not critical and preferred values will depend on the nature of the conductive and carrier materials. The temperature at which the support structure is peeled from the protective layer will depend on the properties of the electrically conductive
20 release layer 16. The support structure can be removed about 1 minute or less, and preferably between about 1 second and about 20 seconds, after lamination without delamination of the protective layer or any of the other component layers.

25 In the preparation of the final image, it is sometimes preferred to keep the support structure in place on the imaged electrographic element throughout storage and processing in order to prevent any damage or marring to the underlying layers. Removal of the base layer is the very
30 last step in preparing and mounting the protected electrographic image. In this instance, the support structure can be removed at room temperature delamination of the protective layer.

Those skilled in the art will readily appreciate that
35 images may be prepared from elements comprising additional or different layers by appropriate modifications of this procedure. For example, if the element comprises adhesive

layer 13 and dielectric layer 15, such as the element depicted in FIG. 3a, instead of combined dielectric/adhesive layer 11, the latent image is formed by depositing the charge on imaging surface 24 of adhesive layer 13, toning the latent image, laminating a receptor to imaging surface 24 to form an element consisting of, in order, base 18, polymeric release layer 16, protective layer 17, dielectric layer 15, adhesive layer 13, the toned image, and the receptor. Removing support structure 14 forms an image comprising, in order, protective layer 17, dielectric layer 15, adhesive layer 13, the toned image, and the receptor.

INDUSTRIAL APPLICABILITY

The elements are useful for the production of images, especially colored images, by electrographic processes. Electrographic imaging is particularly useful for forming large size images, such as are required for banners, billboards, and other out-of-doors advertisements.

EXAMPLES

Glossary

Acrylic resin E-342	Solvent based modified acrylic copolymer (Rohm and Haas, Philadelphia, PA)
Acryloid® A-101	40% solids methyl methacrylate acrylic polymer in methyl ethyl ketone (Tg = 105°C) (Rohm and Haas, Philadelphia, PA)
Ageflex® FA1Q80MC	80% 2-Acryloyloxyethyltrimethylammonium chloride in water (CPS Chemical, Old Bridge, NJ)
Ageflex® FA1Q80DMS	80% 2-Acryloyloxyethyltrimethylammonium dimethylsulfate in water (CPS Chemical, Old Bridge, NJ)
Butvar® B-76	Polyvinyl butyral (weight ave. molecular weight: 90,000-120,000) (Monsanto, St. Louis, MO)
B-CEA	β-Carboxyethyl acrylate
Darocur® 1173	2-Hydroxy-2-methyl-1-phenylpropan-1-one (Ciba Geigy, Hawthorne, NY)

	DMDAC	Dimethyldiallylammonium chloride
	Dowanol® PM	Propylene glycol monomethyl ether (Dow Chemical, Midland, MI)
5	Ebecryl® 350	Polyacrylated polydimethylsiloxane-polyether copolymer having a viscosity of 200-300 centipoise at 25°C (U.C.B. Radcure, Smyrna, GA)
10	Ebecryl® 810	Tetrafunctional polyesteracrylate (U.C.B. Radcure, Smyrna, GA)
15	Ebecryl® 1360	Hexaacrylate of a polydimethylsiloxane-polyether copolymer having a viscosity of 1000-3000 centipoise at 25°C (U.C.B. Radcure, Smyrna, GA)
20	Ebecryl® 1608	Bisphenol A epoxy acrylate & 20% propoxylated glycerol triacrylate (U.C.B. Radcure, Smyrna, GA)
25	Ebecryl® 3200	Blend of aliphatic and aromatic acrylated epoxy resins (U.C.B. Radcure, Smyrna, GA)
	2-HEA	2-Hydroxyethyl acrylate
30	Hydrocarb® PG3	Wet ground calcium carbonate, average particle size of 3 µm (OMYA, Proctor, VT)
	MAPTAC	(3-(Methacryloylamino)propyl)trimethylammonium chloride
35	OK 412	Organic surface treated silica, particle size 5.0 to 7.0 microns (Degussa, Ridgefield Park, NJ)
40	SR 256	2-(2-Ethoxyethoxy)ethyl acrylate (Sartomer, West Chester, PA)
	SR 285	Tetrahydrofurfuryl acrylate (Sartomer, West Chester, PA)
45	PETA	Pentaerythritol triacrylate
	Photomer® 5018	Tetrafunctional polyester acrylate (Henkel, Ambler, PA)
50	Piccolastic® A-5	Low molecular weight polystyrene (Hercules, Wilmington, DE)
55	Syloid® 74	Amorphous silica slurry, average particle size 9 µm (Davison Chemical Division, W.R. Grace, Baltimore, MD)

TMPEOTA

Trimethylolpropaneethoxylate triacrylate

Polymer Characterization

Polymer electrical conductivity is expressed as the surface resistivity of a film of the polymeric material coated on a base, and is expressed in "ohms per square" (Ω/\square). Unless otherwise specified, the following procedures were used to characterize the polymeric materials.

Surface resistivity measurements were made under TAPPI conditions, i.e., at 50% relative humidity at 73°F (23°C), as measured with a probe having a 6.0 inch (about 15.2 cm) x 6.0 inch (about 15.2 cm) area between two 0.50 in² (about 3.2 cm²) square cross-section brass bars connected to a General Radio 1864 Megohmmeter. Each polymeric coating was cut to fit the outside dimensions of the probe and conditioned at 50% relative humidity at 73°F (23°C) for about 1 to 2 hr. before measurement was made.

Surface release characteristic was determined using a Scotch® brand 610 (610 tape) (3M, St. Paul, MN) pressure sensitive contact-adhesive tape (a widely accepted standard for film adhesion testing) and a film of the polymeric material coated on a base. Surface release measurements were made as follows: An 8 in (20.3 cm) long, 1 in (2.54 cm) wide strip of 610 tape was adhered to the surface of the coated polymeric sheet and the excess sheet trimmed from around the adhered tape. The tape was peeled from the coated polymeric sheet at an angle of 180° at a rate of about 25 cm/min using an Instron tester and the peel force required noted. Alternatively, when quantitative measurements were not required, the tape may be stripped manually at an angle of 180° and the relative ease of removal noted. In each instance the surfaces of the polymeric coating and of the adhesive of the stripped tape were inspected for any transfer of adhesive material to the coating surface, or transfer of polymeric material to the tape.

Surface topography of a coated polymeric material depends upon several factors, e.g., coating fluid viscosity,

coating thickness, base roughness, penetration, and the specific coating method used. Surface topography influences the reflectivity of a film of the polymeric material, i.e., its gloss level. Surface gloss measurements were made using
5 a Gardner Laboratory Glossgard II 75° Glossmeter, which measures the amount of specular reflectance of a beam of light from a surface in which the beam of light is incident on the surface at an angle of 75° from the surface plane. Sheffield surface roughness was measured using a Giddiness &
10 Luis Smoothcheck Apparatus.

Viscosity measurements were made using a Brookfield LVT Viscometer with Spindle No. 3 at 30 rpm, and at about 72°F (22°C).

Example 1

15 This example illustrates preparation and imaging of an electrographic element.

To prepare combined electrically conductive release layer 16, a conductive/release coating composition was prepared by mixing the following ingredients with a
20 Lightnin® Mixer.

	<u>Amount (%)</u>	<u>Ingredient</u>
	32.8	Ageflex® FA1Q80MC
	19.9	β-CEA
	19.9	TMPEOTA
25	19.9	Ebecryl® 1608
	0.5	Ebecryl® 350
	5.0	Darocur® 1173

The composition was coated onto 63 g/m² opaque conductive paper (Product OLP, Otis Specialty Papers, Jay, ME) by reverse gravure at a coated weight of 3.0 g/m². The
30 coating was cured using one pass at 100 ft/min (50 cm/sec) under two 300 watts/in (about 125 watts/cm) mercury lamps. An element consisting of electrically conductive release layer 16 and base 18 was produced. Electrically conductive
35 release layer 16 had a 75° gloss of 90-95% and a surface resistivity of 1.5 Mohm/□ at 50% relative humidity and 23°C. The surface energy was about 23 dyne/cm.

Combined transparent dielectric/adhesive 11 was prepared from the following ingredients.

	<u>Ingredient</u>	<u>Parts by Weight</u>
	Ethanol	120
5	Acetone	440
	Toluene	720
	Butvar® B-76	130
	Acrylic Resin E-342	440
	Syloid® 74	20
10	Hydrocarb® PG3	175
	Piccolastic® A-5	52

The first three listed ingredients were added to a Kady mill and the Butvar® was stirred in. After 15 min. of mixing the acrylic resin and the polystyrene were added. 15 After a further 5 min. of mixing, the calcium carbonate and the amorphous silica were added and the mixing continued for 10 min. The resulting mixture was applied to electrically conductive release layer 16 by reverse roll coating and dried at 115-130°F (about 46-54°C) to give a dry coat weight 20 of 5 g/m². A element consisting of base 18, electrically conductive release layer 16, and combined transparent dielectric/adhesive 11 was produced. The Sheffield surface roughness was 75 to 80 sec/100 mL. The dielectric coating could be completely removed from electrically conductive 25 release layer 16 by mild pulling with Scotch® Brand Magic Tape (810 tape) (3M, St. Paul, MN).

The electrographic element was moisturized to a level of about 6% by weight and a four color image layer was deposited on combined transparent dielectric/adhesive 11 30 using a Raster Graphics DCS 5400 printer (Raster Graphics, San Jose, CA) and standard toners and plotting conditions. A high quality four color image was produced.

The imaged element was laminated onto a receptor by first laying the imaged electrographic element on a receptor 35 sheet of ScotchCal® 7725 pressure sensitive vinyl (3M Commercial Graphics, St. Paul, MN) with the toned image in contact with the receptor sheet. This composite was then

passed through the hot nip of an Orca® III hot nip laminator (Pro-Tech Engineering, Madison, WI) at a speed of 2 ft/min (0.61 m/min), 240°F (116°C) and a cylinder pressure of 100 psi (7.03 Kg/cm²). The support base was removed
5 approximately 10 sec. after the laminated composite was removed from the hot nip. The toned image transferred completely. It had a 75° gloss of 80 to 90%.

Example 2

This example illustrates preparation and imaging of an
10 electrographic element. Electrically conductive release layer 16 was cured in an oxygen depleted atmosphere to produce a glossy product.

The electrically conductive release coating composition described in Example 1 was coated onto 60 g/m² opaque
15 conductive paper (Product DR Base, Otis Specialty Papers, Jay, ME) by reverse gravure with a 200 RBH gravure cylinder at a coated weight of 3.1 g/m². The coating was cured under 600 watts/in (about 250 watts/cm) ultraviolet irradiation at 900 ft/min (about 460 cm/sec) in an inerted atmosphere
20 (oxygen concentration less than 50 ppm). An element consisting of electrically conductive release layer 16 and base 18 was produced. Electrically conductive release layer 16 had a 75° gloss of 92-95% and a surface resistivity of 1.6 Mohm/□ at 50% relative humidity and 23°C. The surface
25 energy was about 23 dyne/cm.

Combined transparent dielectric/adhesive 11 was prepared as described in Example 1 and coated onto electrically conductive release layer 16 with a #16 Mayer rod to produce an element consisting of base 18, combined
30 conductive/release layer 16, and combined transparent dielectric/adhesive layer 11. The dielectric coating could be readily removed from electrically conductive release layer 16 by mild pulling with 810 tape.

Rolls of the electrographic element were moisturized to
35 a level of from 6 to 7% by weight. A four color toned image layer was deposited on combined transparent dielectric/adhesive layer 11 using a Versatec® 8944 Color

Electrostatic Printer (Xerox ColorgrafX Systems, San Jose, CA) using standard toners and coating conditions.

The imaged element was laminated onto a receptor of ScotchCal® 7725 pressure sensitive vinyl as described in Example 1. The toned image transferred completely.

Example 3

This example illustrates preparation and imaging of an imaging element using a conductive release coating with a glossy finish.

The following composition was prepared and coated onto Otis OLP conductive paper by reverse gravure using a laboratory scale web coater. The coating was cured by a exposure to two 300 watt ultraviolet lamps (about 120 watts/cm) at a speed of about 18-20 cm/sec.

<u>Component</u>	<u>Parts</u>
Ageflex® FA1Q80MC	75
Ebecryl® 1608	20
Darocur® 1173	4
Ebecryl® 350	1

Surface resistivity was $3.9 \times 10^6 \Omega/\square$. Gloss was 91%. Sheffield surface roughness was 50 sec/100 mL. Surface energy was about 23 dyne/cm.

The dielectric/adhesive layer described in Example 1 was coated onto the conductive layer as described in Example 1. Black and white images were prepared and transferred to an adhesive substrate as described in Example 2. The toned image transferred completely. The image had acceptable image density, gloss, and aesthetic properties.

Example 4

This example illustrates preparation and imaging of an imaging element using a conductive release coating with a matte finish.

The following composition was prepared, coated, and evaluated by the procedure described in Example 3.

<u>Component</u>	<u>Parts</u>
Ageflex® FA1Q80MC	70
Ebecryl® 1608	19

Darocur® 1173	4
Ebecryl® 350	1
OK 412	6

Surface resistivity was $5.3 \times 10^6 \Omega/\square$. Gloss at 75° was
5 27%. Sheffield surface roughness was 80 sec/100 mL.
Surface energy was about 23 dyne/cm. The conductive coating
was overcoated with a dielectric layer, imaged, and the
image transferred as described in Example 3. The toned
image transferred completely. The image had acceptable
10 image density, gloss, and aesthetic properties.

Example 5

This example illustrates preparation and imaging of an
electrographic element. Electrically conductive release
layer 16 was cured in an oxygen depleted atmosphere to
15 produce a matte product.

The electrically conductive release coating composition
described in Example 2 was coated onto 60 g/m^2 opaque
conductive paper (Product DR Base, Otis Specialty Papers,
Jay, ME) by direct gravure with a 180 RBH gravure cylinder
20 at a coated weight of 2.3 g/m^2 . The coating was cured under
300 watts/in (about 125 watts/cm) ultraviolet irradiation at
500 ft/min (about 250 cm/sec) in an inerted atmosphere
(oxygen concentration less than 50 ppm). An element
consisting of electrically conductive release layer 16 and
25 base 18 was produced. Electrically conductive release layer
16 had a 75° gloss of 45-50% and a surface resistivity of
 $1.4 \text{ Mohm}/\square$ at 50% relative humidity and 23°C . The surface
energy was about 23 dyne/cm.

Combined transparent dielectric/adhesive 11 was
30 prepared as described in Example 1 and coated onto
electrically conductive release layer 16 with a #16 Mayer
rod to produce an element consisting of base 18,
electrically conductive release layer 16, and combined
transparent dielectric/adhesive layer 11. The dielectric
35 coating could be readily removed from electrically
conductive release layer 16 by mild pulling with 810 tape.

A four-color toned image layer was deposited on

combined transparent dielectric/adhesive layer 11 as described in Example 4. The imaged element was laminated onto a receptor of ScotchCal® 7725 pressure sensitive vinyl as described in Example 1. The toned image transferred
5 completely.

Example 6

This example illustrates preparation and imaging of an electrographic element. Electrically conductive release layer 16 was cured by an electron beam in an oxygen depleted
10 atmosphere to produce a matte product.

The electrically conductive release coating composition described in Example 1 was coated onto 60 g/m² opaque conductive paper (Product DR Base, Otis Specialty Papers, Jay, ME) by direct gravure with a 200 RBH gravure cylinder
15 at a coated weight of 1.3 g/m². The coating was cured by electron beam radiation at 0.5 Mrad at 1000 ft/min (about 500 cm/sec) in an inerted atmosphere (oxygen concentration less than 50 ppm). An element consisting of electrically conductive release layer 16 and base 18 was produced.
20 Electrically conductive release layer 16 had a 75° gloss of 19-20% and a surface resistivity of 1.5 Mohm/□. The surface energy was about 23 dyne/cm.

A four-color toned image layer was deposited on combined transparent dielectric/adhesive layer 11 as
25 described in Example 4. The imaged element was laminated onto a receptor of ScotchCal® 7725 pressure sensitive vinyl as described in Example 1. The freshly formed toned image transferred completely.

Example 7

30 This example illustrates a precursor-rich formulation comprising a coupling solvent that can be used to form electrically conductive polymeric release layer 16.

The following composition gave a clear coating solution that was coated onto DR base using a #16 Mayer rod and cured
35 using two passes at 100 ft/min (50 cm/sec) under two 300 watts/in (about 125 watts/cm) mercury lamps in an RPC laboratory ultraviolet processor.

	<u>Grams</u>	<u>Component</u>
	6.0	50 wt% aq MAPTAC
	5.0	2-HEA
	2.0	PETA
5	4.0	Dowanol® PM
	1.0	Ebecryl® 350
	0.6	Darocur® 1173

A film surface that had very easy release from 610 tape was produced. The surface resistivity was $1.5-2.0 \times 10^6 \Omega/\square$ (the base paper alone was $2.5 \times 10^6 \Omega/\square$). The was gloss of 77% at 75°.

Example 8

This example illustrates a composition comprising oligomeric acrylates to improve cure rate and physical properties that can be used to form electrically conductive polymeric release layer 16.

A coating composition was prepared from the following components.

	<u>Grams</u>	<u>Component</u>
20	7.5	Ageflex® FA1Q80MC
	2.0	N-vinyl pyrrolidone
	6.0	Pentaerythritoltriacrylate
	6.0	2-Ethoxyethoxyethylacrylate
	1.2	Darocur® 1173
25	0.16	Ebecryl® 350
	2.0	Water

The coating composition was thoroughly shaken to obtain a dispersion which was coated on the DR base paper with a #6 Mayer rod and cured with two passes under two 400 watts per inch (about 160 watts/cm) mercury vapor lamps at a speed of 100 ft/min (about 50 cm/sec). The cured coating had a gloss of 89-92% at 75°, surface resistivity of $1.5-2.0 \times 10^6 \Omega/\square$, and gave easy 610 tape release.

Example 9

This example illustrates a composition that can be used to form electrically conductive polymeric release layer 16. A stable clear coating was prepared from the following components.

	<u>Grams</u>	<u>Component</u>
	7.50	Ageflex® FA1Q80MC
	10.0	2-Hydroxypropylacrylate
	4.0	Pentaerythritol triacrylate
10	1.2	Darocur® 1173
	0.11	Ebecryl® 350
	3.5	Water
	2.0	Butyl Carbitol®

The composition was coated with a #0 Mayer rod onto DR base and cured with two passes at 100 ft/min (50 cm/sec) using two 300 watts/in (125 watts/cm) mercury lamps. A glossy, dry, tack-free coating that had resistivity of $5.3 \times 10^5 \Omega/\square$ and readily released 610 tape was obtained.

The solution was coated onto non-conductive polyethylene terephthalate film (PET) using a #36 Mayer Rod and cured with three passes at 100 ft/min (50 cm/sec) using two 300 watts/in (125 watts/cm) mercury lamps. A dry, glossy 0.056 mm thick transparent coating was obtained having a resistivity of $5.3 \times 10^5 \Omega/\square$.

Example 10

This example illustrates a composition that can be used to form electrically conductive polymeric release layer 16. A very nearly clear coating solution was prepared from the following components.

	<u>Grams</u>	<u>Component</u>
	7.50	Ageflex® FA1Q80MC
	2.0	Pentaerythritol triacrylate
	4.0	N-Vinyl pyrrolidone
	0.16	Ebecryl® 350
35	0.75	Darocur® 1173
	2.0	Butyl Carbitol®

The composition was coated on DR base sheet with a #14

Mayer Rod and cured with two passes at 100 ft/min (50 cm/sec) under two 400 watts/in about 160 watts/cm) mercury lamps. The cured coating had 94% gloss at 75°, surface resistivity of $0.7-0.8 \times 10^6 \Omega/\square$, and good, complete 610 tape release.

Example 11

This example illustrates that some combinations of water miscible precursors that are immiscible with concentrated aqueous quaternary precursors can be used to form electrically conductive polymeric release layer 16 if limited dilution with water is made and surfactant type acrylated siloxanes are used both for release and dispersion. A coating mixture was prepared from the following components.

15	<u>Grams</u>	<u>Component</u>
	7.5	Ageflex® FA1Q80MC
	2.0	N-Vinyl pyrrolidone
	6.0	Pentaerythritol triacrylate
	6.0	2-Ethoxyethoxyethylacrylate
20	1.2	Darocur® 1173
	0.1	Ebecryl® 350
	2.0	Water

The mixture was thoroughly shaken to obtain a dispersion that was coated on the DR base with a #6 Mayer rod and cured as in Example 10. The cured coating had a gloss of 89-92% at 75°, surface resistivity of $1.5-2.0 \times 10^6 \Omega/\square$, and gave easy 610 tape release.

Example 12

This example illustrates use of a dispersion not employing extra water to provide a clear thin layer that can be used to form electrically conductive polymeric release layer 16. A coating mixture was prepared from the following components.

35	<u>Grams</u>	<u>Component</u>
	7.5	Ageflex® FA1Q80MC
	6.0	Tetrahydrofurfurylacrylate
	6.0	Pentaerythritol triacrylate

2.0	N-Vinylpyrrolidone
1.2	Darocur® 1173 + 10% benzophenone
0.32	Ebecryl® 350

The mixture was coated on the DR base with a #0 Mayer rod and cured as in Example 10. The cured coating had 80% gloss at 75°, a surface resistivity of $2.5-4.5 \times 10^6 \Omega/\square$, and easy 610 tape release. A similar formulation, in which Ebecryl® 350 was used in place of 0.45 g Ebecryl® 1360 acrylated siloxane, also performed well.

Example 13

This example illustrates the use of a very high weight level of quaternary salt precursor to form a layer that can be used to form electrically conductive polymeric release layer 16. A coating mixture was prepared from the following components.

<u>Parts</u>	<u>Component</u>
10.0	Ageflex® FA1Q80MC
2.0	TMPEOTA
0.50	Darocur® 1173
0.10	Ebecryl® 350
0.10	Ebecryl® 1360

The hazy dispersion was coated onto non-conductive Champion 60-lb litho paper with a #0 Mayer rod and cured as described in Example 10. The coating had a resistivity of $1.3 \times 10^5 \Omega/\square$.

Example 14

This example illustrates the facile polymerization of a typical dispersion lacquer using an electron beam and no photoinitiator to form a layer that can be used to form electrically conductive polymeric release layer 16. A coating mixture was prepared from the following components.

<u>Parts</u>	<u>Component</u>
264.0	Ageflex® FA1Q80MC
160.0	B-CEA
160.0	TMPEOTA
176.0	Ebecryl® 1608
8.0	Ebecryl® 350

8.0 Ebecryl® 1360

The dispersion was coated onto DR base paper with a #0 Mayer rod and cured at four increasingly lower dose levels at 30 ppm oxygen. Even at the lowest dose, a full dry cure was obtained. The uncoated DR base paper has a resistivity of $2.5 \times 10^6 \Omega/\square$.

	<u>Dose in Megarads</u>	<u>Resistivity (Ω/\square)</u>
	3	$0.7-0.8 \times 10^6$
	2	$0.6-0.8 \times 10^6$
10	1	$0.6-0.8 \times 10^6$
	0.5	$0.6-0.8 \times 10^6$

Example 15

This example illustrates use of a carboxylated precursor in conjunction with a quaternary salt conductivizing agent. A coating mixture was prepared from the following components:

	<u>Parts</u>	<u>Component</u>
20	33.04	Ageflex® FA1Q80MC
	17.62	β -carboxyethylacrylate
	17.62	TMPEOTA
25	4.42	Photomer® 5018
	22.02	Ebecryl® 1608
30	5.28	Darocur® 1173 and 10% benzophenone
	2.80(3%)	Ebecryl® 350
	1.87(2%)	Ebecryl® 1360

The dispersion was coated onto DR base paper with a smooth (#0) Mayer Rod and cured dry in one pass at 300 ft/min (150 cm/sec) under two 300 watts/inch (about 120 watts/cm) mercury lamps.

Mix Viscosity: 440 cps
 Resistivity: $0.6 \times 10^6 \Omega/\square$
 Peel Force: 15-25 g/in (38-64 g/cm)

Example 16

This example illustrates the use of a non-acrylic ethylenically unsaturated free-radical polymerizable quaternary salt precursor in the coating mixture. For comparative purposes, DMDAC was used in an amount equimolar to the Ageflex® FA1Q80MC of Example 15. A coating mixture was prepared from the following components:

	<u>Parts</u>	<u>Component</u>
10	36.37	60% aq.soln. of DMDAC
	20	β-CEA
	20	TMPEOTA
15	22	Ebecryl® 1608
	5.3	Darocur® 1173
20	1.0	Ebecryl® 350

The hazy dispersion was coated onto DR base paper with a #0 Mayer rod and onto polyethylene terephthalate film with a #36 Mayer rod and cured using two 300 watts/in (about 120 watts/in) mercury lamps and one pass at 200 ft/min (100 cm/sec) and two passes at 100 ft/min (50 cm/sec). The cured coatings were both glossy and dry-to-touch. The coating on the film were transparent though hazy. Both coatings released 610 tape well. The paper coating had a resistivity of $5 \times 10^5 \Omega/\square$. The film coating had a resistivity of $10 \times 10^6 \Omega/\square$.

Having described the invention, we now claim the following and their equivalents.

CLAIMS

What is claimed is:

- 5 1. An imaging element comprising a support structure and an imaging layer structure wherein the support structure is removably adhered to the imaging layer structure and wherein the support structure comprises an electrically
10 conductive polymeric release layer having tailored optical and surface release properties comprising, in polymerized form:
- (A) 1 to 80 weight parts of a polymerizable, ethylenically unsaturated ammonium precursor;
- 15 (B) 0.1 to 10 weight parts of a polymerizable, ethylenically unsaturated, organo-silicone precursor;
- (C) 5 to 95 weight parts of a multifunctional polymerizable precursor containing at least two
20 polymerizable, ethylenically unsaturated functional groups;
- (D) 0 to 60 weight parts of a polymerizable, ethylenically unsaturated acidic precursor containing at least one carboxylic acid group; and
- 25 (E) 0 to 90 weight parts of a monofunctional precursor containing one polymerizable, ethylenically unsaturated functional group.
2. The element of claim 1 wherein said electrically conductive polymeric release layer has a thickness between about 1 micron to about 20 microns and an electrical
30 resistance between about $1 \times 10^5 \Omega/\square$ and $1 \times 10^8 \Omega/\square$.
3. The element of claim 2 wherein said electrically conductive polymeric release layer has a surface energy of between 20 and 40 dynes/cm².
4. The element of claim 1 wherein said polymerizable,
35 ethylenically unsaturated ammonium precursor contains a cation selected from the group consisting of (3-(methacryloylamino)propyl)trimethylammonium, (2-(methacryloyl-

oxy)ethyl)trimethylammonium, (2-(acryloyloxy)ethyl)-trimethylammonium, (2-(methacryloyloxy)ethyl)methyldiethylammonium, 4-vinylbenzyltrimethylammonium, dimethyldiallylammonium, and mixtures thereof.

5 5. The element of claim 4 wherein the ammonium precursor is 2-(acryloyloxy)-ethyltrimethylammonium chloride.

6. The element of claim 1 wherein said polymerizable, ethylenically unsaturated, organo-silicone precursor is an
10 acrylated-oxyalkylene-silicone precursor wherein the alkylene is ethylene, propylene or a combination thereof.

7. The element of claim 6 wherein the multifunctional polymerizable precursor is a multifunctional monomeric material, an oligomeric material, or a combination thereof.

15 8. The element of claim 1 wherein said element is an electrographic imaging element.

9. The element of claim 7 wherein said element is an electrographic element,
wherein said support structure comprises, in order:

20 (1) a base, and
 (2) said electrically conductive polymeric release layer, and

wherein said imaging layer structure comprises, in order:

 (3) a protective layer,
25 (4) a dielectric layer, and
 (5) an adhesive layer, and

wherein said electrically conductive polymeric release layer is removably adhered to said protective layer.

10. The element of claim 9 wherein said electrically
30 conductive polymeric release layer has a thickness between about 1 micron and about 20 microns and an electrical resistance between about $1 \times 10^5 \Omega/\square$ and $1 \times 10^8 \Omega/\square$.

11. The element of claim 10 wherein said electrically conductive polymeric release layer has a surface energy of
35 between 20 and 40 dynes/cm².

12. The element of claim 11 wherein said dielectric layer and said adhesive layer are combined in a single

dielectric/adhesive layer whose dielectric constant is between about 2 and 5 and whose adhesive properties are activated at a temperature above ambient temperature.

13. The element of claim 12 wherein said
5 dielectric/adhesive layer comprises one or more materials selected from the group consisting of polyurethanes; polyamides; polyolefins; polycarbonates; polystyrenes; polymers or copolymers of acrylic acid, methacrylic acid, acrylic esters, methacrylic esters, acrylic amides,
10 methacrylic amides, styrenes, acrylonitriles, vinyl esters, alkyd substituted vinyl esters, vinyl alcohol, vinyl acetals, vinyl chloride, vinyl fluoride, vinylidene chloride, and 1,4-dienes; ethylene/vinyl alcohol copolymers; copolymers of styrene with acrylic and methacrylic monomers;
15 modified cellulosic resins; and block copolymer thermoplastic rubbers.

14. The element of claim 12 wherein said protective layer consist essentially of a fluoropolymer and an acrylic polymer.

20 15. The element of claim 14 wherein said electrically conductive polymeric release layer has a thickness between about 1 micron and about 20 microns, an electrical resistance between about $1 \times 10^5 \Omega/\square$ and $1 \times 10^8 \Omega/\square$, and a surface energy of between 20 and 40 dynes/cm².

25 16. The element of claim 15 wherein said polymerizable, ethylenically unsaturated, organo-silicone precursor is an acrylated-oxyalkylene-silicone precursor wherein the alkylene is ethylene, propylene or a combination thereof.

30 17. The element of claim 9 wherein said support structure additionally comprises a second electrically conductive polymeric release layer and wherein said support structure comprises, in order: said second electrically conductive polymeric release layer, said base, and said
35 electrically conductive polymeric release layer.

18. The element of claim 1 wherein a liquid precursor mixture comprising precursors (A) through (C) and precursors

(D) and (E), if present, is coated to form a coated liquid precursor mixture, and following coating, said coated liquid precursor mixture is cured to form said polymeric conductive/release layer.

5 19. The element of claim 18 wherein said liquid precursor mixture is dissolved in a coupling solvent.

20. The element of claim 19 wherein said coupling solvent is selected from the group consisting of water, water miscible organic solvents, and mixtures thereof.

10 21. The element of claim 20 wherein said water miscible organic solvent is selected from the group consisting of diethylene glycol ethyl ether, diethylene glycol butyl ether, tetrahydrofurfuryl alcohol, γ -butyrolactone, and 1-methoxy-2-propanol.


15 22. The element of claim 18 wherein said precursor mixture is a stable, homogeneous, liquid dispersion.

23. The element of claim 18 wherein a liquid precursor mixture is cured to form said polymeric conductive/release layer by irradiation with an electron beam.

20 24. The element of claim 18 wherein a liquid precursor mixture is cured to form said polymeric conductive/release layer by irradiation with ultraviolet light.

25 25. The element of claim 7 wherein said electrically conductive release layer comprises 60 to 80 weight parts of said ethylenically unsaturated ammonium precursor and 0.2 to 2 weight parts of said polymerizable, ethylenically unsaturated, organo-silicone precursor.

26. The element of claim 25 wherein said ethylenically unsaturated ammonium precursor is:



in which R_1 is H, methyl, or ethyl; Y is $-\text{O}-$ or $-(\text{NR}_3)-$,
 35 wherein R_2 is H or a C_1-C_4 alkyl; m is an integer from 1 to 4, each R_2 individually is a C_1-C_4 alkyl group; and $[\text{X}]^-$ is an anion.

27. The element of claim 25 wherein said electrically

conductive polymeric release layer additionally comprises 1 to 20 weight parts of amorphous silica, based on the total weight of the polymerizable materials.

28. A method for forming an image comprising, in
5 order:

(1) forming a latent image of electrostatic charge on the surface of an imaging layer structure of an imaging element comprising a support structure and said imaging layer structure,

10 wherein said support structure is removably adhered to said imaging layer structure and wherein said support structure comprises an electrically conductive polymeric release layer having tailored optical and release properties
15 comprising, in polymerized form:

(A) 1 to 80 weight parts of a polymerizable, ethylenically unsaturated ammonium precursor;

20 (B) 0.1 to 10 weight parts of a polymerizable, ethylenically unsaturated, organo-silicone precursor;

(C) 5 to 95 weight parts of a multifunctional polymerizable precursor containing at least two polymerizable, ethylenically unsaturated functional groups;

25 (D) 0 to 60 weight parts of a polymerizable, ethylenically unsaturated acidic precursor containing at least one carboxylic acid group; and

30 (E) 0 to 90 weight parts of a monofunctional precursor containing one polymerizable, ethylenically unsaturated functional group;

(2) toning said latent image to produce a toned image on said surface of said imaging layer structure:

35 (3) laminating a receptor to said surface of said imaging layer structure to produce an element comprising, in order, said receptor, said toned image, said imaging layer structure, and said

support structure;

- (4) removing said support structure to produce said image, said image comprising, in order, said receptor, said toned image, and said imaging layer structure,

wherein said electrically conductive polymeric release layer has a thickness between about 1 micron and about 20 microns, an electrical resistance between about $1 \times 10^5 \Omega/\square$ and $1 \times 10^8 \Omega/\square$, and a surface energy of between 20 and 40 dynes/cm².

29. The method of claim 25 wherein said imaging element is an electrographic element, wherein said support structure comprises, in order:

- (1) a base, and
(2) said electrically conductive polymeric release layer, and

wherein said imaging layer structure comprises, in order,

- (3) a protective layer,
(4) a dielectric layer, and
(5) an adhesive layer;

wherein said electrically conductive polymeric release layer is removably adhered to said protective layer.

30. The method of claim 26 wherein said dielectric layer and said adhesive layer are combined in a single dielectric/adhesive layer whose dielectric constant is between about 2 and 5 and whose adhesive properties are activated at a temperature above ambient temperature.




FIGURE 1




FIGURE 2a




FIGURE 2b




FIGURE 3a




FIGURE 3b




FIGURE 4

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US97/06511

A. CLASSIFICATION OF SUBJECT MATTER IPC(6) : G03G 5/00; B44C 1/00 US CL : 399/342; 156/240, 241, 230, 247; 347/114, 153; 428/354 According to International Patent Classification (IPC) or to both national classification and IPC																				
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) U.S. : 399/342; 156/240, 241, 230, 247; 347/114, 153; 428/354 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) APS search terms quarternary ammoni##; organo silicone# or organosilicone; conductive; imag?																				
C. DOCUMENTS CONSIDERED TO BE RELEVANT																				
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.																		
A	US 4,981,729A (ZALESKI) 01 January 1991	NONE																		
A	US 5,483,321A (CAHILL et al) 09 January 1996																			
A	US 5,414,502A (CAHILL et al) 09 May 1995																			
A	US 4,420,541A (SHAY) 13 December 1983																			
A,P	US 5,621,057A (HERZIG et al) 15 April 1997																			
A	US 5,400,126A (CAHILL et al) 21 March 1995																			
A	US 5,486,421A (KOBAYASHI et al) 23 January 1996																			
A	US 5,035,849A (UEMURA et al) 30 July 1991																			
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.																				
<table border="0"> <tr> <td>* Special categories of cited documents:</td> <td>*T</td> <td>later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</td> </tr> <tr> <td>*A* document defining the general state of the art which is not considered to be of particular relevance</td> <td>*X*</td> <td>document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</td> </tr> <tr> <td>*E* earlier document published on or after the international filing date</td> <td>*Y*</td> <td>document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</td> </tr> <tr> <td>*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</td> <td>*G*</td> <td>document member of the same patent family</td> </tr> <tr> <td>*O* document referring to an oral disclosure, use, exhibition or other means</td> <td></td> <td></td> </tr> <tr> <td>*P* document published prior to the international filing date but later than the priority date claimed</td> <td></td> <td></td> </tr> </table>			* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	*A* document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	*E* earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*G*	document member of the same patent family	*O* document referring to an oral disclosure, use, exhibition or other means			*P* document published prior to the international filing date but later than the priority date claimed		
* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention																		
A document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone																		
E earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art																		
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*G*	document member of the same patent family																		
O document referring to an oral disclosure, use, exhibition or other means																				
P document published prior to the international filing date but later than the priority date claimed																				
Date of the actual completion of the international search 14 AUGUST 1997		Date of mailing of the international search report 05 SEP 1997																		
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230		Authorized officer <i>Jenna Davis</i> JENNA DAVIS Telephone No. (703) 308-2351																		

